



your partner in fluoropolymers



Technical Data Sheet

NORGLIDE[®] MP4 Type 500400

FOR INFORMATION ONLY

Data Sheet updates will not be circulated.

1. **Product** : Semi-finished **NORGLIDE[®] MP**
2. **Composition** : Sliding bearing material, consisting of PTFE compound sintered into a flexible metal mesh backing.
3. **Components** :
 - a) PTFE compound with approximately 30% of filler content of glass fibres and graphite.
 - b) Stabilized CuSn6 mesh, material no. 2.1020 to DIN 17662, from wires of 0.40mm diameter. The mesh is linked at intersections and has a thickness after calendering of 0.7mm. The mesh count in warp and weft direction is 11 ± 1 per cm.
4. **Dimensions** : As tape in meters wound on reels

Width (nominal)	:	320mm (useful \leq 310mm)
Thickness	:	0.78 ± 0.020 mm

5. Material Related Characteristics

Properties	Test Method	Unit	Value
Density (total)	DIN 53479	g/cm ³	4.15 – 4.65
Tensile Strength	DIN EN ISO 527-3	N/mm ²	≥ 45
Elongation at Break	DIN EN ISO 527-3	%	≥ 10

6. Application Related Characteristics

Maximum Admissible Specific Bearing Load	Static Dynamic	N/mm ² N/mm ²	100 80
Coefficient of Friction at RT Measured on Steel with ≥ 58 HRC	at 4.8 N/mm ² and 0.058 m/s at 70 N/mm ² and 0.0065 m/s		0.17 0.09
k Factor		10 ⁻⁶ mm ³ /Nm	
Deformation Under Load	23°C, at 100 N/mm ² , 1h	μ m	≤ 50
Rate of Heat Transfer	SG PA 3/1300/3022	W/m ² K	800
Service Temperature Range	Permanent Intermittently	°C	-200 - +260 300
Coefficient of Linear Thermal Expansion	SG PA 0/1320/1025	10 ⁻⁵ K ⁻¹	13
Surface Related Volume Resistance	SG PA 1/1320/1081	Ω cm ²	$\geq 10^8$

Data are typical performance values of laboratory tests, must not be considered as specification for constructions.

Norglide[®] is a registered trade mark of Saint Gobain Performance Plastics

The data listed falls within the normal range of product properties but they should not be used to establish specification limits nor used alone as the basis of design. Polyflon Technology Limited assumes no responsibility for any advice furnished by it or for results obtained with respect to these products. All such advice is provided gratis and the buyer assumes sole responsibility for the results obtained in reliance thereon.